

SILICA-BASED SOLS**Publication number:** WO0066491**Publication date:** 2000-11-09**Inventor:** PERSSON MICHAEL (SE); TOKARZ MAREK (SE); DAHLGREN MAJ-LIS (SE)**Applicant:** AKZO NOBEL NV (NL); EKA CHEMICALS AB (SE); PERSSON MICHAEL (SE); TOKARZ MAREK (SE); DAHLGREN MAJ LIS (SE)**Classification:****- international:** **C01B33/141; C01B33/143; C01B33/146; D21H21/10;**
D21H17/29; D21H17/37; D21H17/45; D21H17/68;
C01B33/00; D21H21/10; D21H17/00; (IPC1-7):
C01B33/143; C01B33/146; D21H21/10**- european:** C01B33/146; C01B33/141; C01B33/143B**Application number:** WO2000SE00821 20000428**Priority number(s):** EP19990850074 19990504; EP19990850160 19991029;
SE19990001687 19990506; US19990132359P
19990504; US19990162445P 19991029**Also published as:**WO0066492 (A1)
CA2371494 (A1)
CA2371492 (A1)
AU766747B (B2)
AU758165B (B2)**Cited documents:**WO9405596
WO9107350
WO9405595
US2750345
GB663013
more >>**Report a data error here****Abstract of WO0066491**

The invention relates to an aqueous sol containing silica-based particles which has an S-value within the range of from 10 to 45 %, a viscosity within the range of from 5 to 40 cP, and a molar ratio of SiO₂ to M₂O, where M is alkali metal or ammonium, within the range of from 10:1 to 40:1, or a silica content of at least 10 % by weight. The invention further relates to a process for the production of silica-based particles comprising the steps of: (a) acidifying an aqueous silicate solution to a pH of from 1 to 4 to form an acid sol; (b) alkalising the acid sol at an SiO₂ content within the range of from 4.5 to 8 % by weight to; (c) allowing particle growth of the alkalisol for at least 10 minutes, or heat-treating the alkalisol at a temperature of at least 30 DEG C; and then (d) alkalising the obtained sol to a pH of at least 10.0. The invention further relates to silica-based particles obtainable by the process, the use of the silica-based particles as drainage and retention aids in the production of paper as well as a process for the production of paper from an aqueous suspension containing cellulosic fibres, and optional filler, in which silica-based particles and at least one charged organic polymer are added to the cellulosic suspension.

Data supplied from the **esp@cenet** database - Worldwide



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : C01B 33/143, 33/146, D21H 21/10	A1	(11) International Publication Number: WO 00/66491 (43) International Publication Date: 9 November 2000 (09.11.00)
(21) International Application Number: PCT/SE00/00821 (22) International Filing Date: 28 April 2000 (28.04.00) (30) Priority Data: 99850074.8 4 May 1999 (04.05.99) EP 60/132,359 4 May 1999 (04.05.99) US 9901687-5 6 May 1999 (06.05.99) SE 99850160.5 29 October 1999 (29.10.99) EP 60/162,445 29 October 1999 (29.10.99) US (71) Applicant (for all designated States except US): AKZO NOBEL N.V. [NL/NL]; P.O. Box 9300, NL-6800 SB Arnhem (NL). (71) Applicant (for SE only): EKA CHEMICALS AB [SE/SE]; S-445 80 Bohus (SE). (72) Inventors; and (75) Inventors/Applicants (for US only): PERSSON, Michael [SE/SE]; Rörviksgatan 51, S-421 65 Västra Frölunda (SE). TOKARZ, Marek [SE/SE]; Håkansgatan 4, S-442 39 Kungälv (SE). DAHLGREN, Maj-Lis [SE/SE]; Kapri-folgången 9, S-449 33 Nödinge (SE). (74) Agent: NYANDER, Johan; Eka Chemicals AB, Patent Department, P.O. Box 11556, S-100 61 Stockholm (SE).		(81) Designated States: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: SILICA-BASED SOLS (57) Abstract <p>The invention relates to an aqueous sol containing silica-based particles which has an S-value within the range of from 10 to 45 %, a viscosity within the range of from 5 to 40 cP, and a molar ratio of SiO₂ to M₂O, where M is alkali metal or ammonium, within the range of from 10:1 to 40:1, or a silica content of at least 10 % by weight. The invention further relates to a process for the production of silica-based particles comprising the steps of: (a) acidifying an aqueous silicate solution to a pH of from 1 to 4 to form an acid sol; (b) alkalising the acid sol at an SiO₂ content within the range of from 4.5 to 8 % by weight to; (c) allowing particle growth of the alkalised sol for at least 10 minutes, or heat-treating the alkalised sol at a temperature of at least 30 °C; and then (d) alkalising the obtained sol to a pH of at least 10.0. The invention further relates to silica-based particles obtainable by the process, the use of the silica-based particles as drainage and retention aids in the production of paper as well as a process for the production of paper from an aqueous suspension containing cellulosic fibres, and optional filler, in which silica-based particles and at least one charged organic polymer are added to the cellulosic suspension.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Silica-based sols

The present invention generally relates to silica-based sols suitable for use in papermaking. More particularly, the invention relates to silica-based sols and silica-based particles, their production and their use in the production of paper. The process of this invention provides silica-based particles and sols containing silica-based particles with high drainage and retention performance, high stability and high solids contents.

Background

In the papermaking art, an aqueous suspension containing cellulosic fibres, and optional fillers and additives, referred to as stock, is fed into a headbox which ejects the stock onto a forming wire. Water is drained from the stock through the forming wire so that a wet web of paper is formed on the wire, and the paper web is further dewatered and dried in the drying section of the paper machine. Drainage and retention aids are conventionally introduced into the stock in order to facilitate drainage and to increase adsorption of fine particles onto the cellulosic fibres so that they are retained with the fibres on the wire.

Silica-based particles are widely used as drainage and retention aids in combination with charged organic polymers like anionic and cationic acrylamide-based polymers and cationic and amphoteric starches. Such additive systems are disclosed in U.S. Patent Nos. 4,388,150; 4,961,825; 4,980,025; 5,368,833; 5,603,805; 5,607,552; and 5,858,174; and International Patent Application WO 97/18351. These systems are among the most efficient drainage and retention aids now in use.

Silica-based particles suitable for use as drainage and retention aids are normally supplied in the form of aqueous colloidal dispersions, so-called sols. Commercially used silica-based sols usually have a silica content of about 7 to 15% by weight and contain particles with a specific surface area of at least 300 m²/g. Sols of silica-based particles with higher specific surface areas are usually more dilute to improve storage stability and avoid gel formation.

It would be advantageous to be able to provide silica-based sols and particles with further improved drainage and retention performance and even better stability. It would also be advantageous to be able to provide a process for preparing silica-based sols and particles with improved drainage, retention and stability properties. It would also be advantageous to be able to provide a papermaking process with improved drainage and/or retention.

The Invention

In accordance with the present invention there are provided silica-based sols and particles which are suitable for use as flocculating agents in water purification and as

drainage and retention aids in papermaking. The silica-based sols and particles according to the invention exhibit good stability over extended periods of time, notably high surface area stability and high stability to avoid gel formation, and hence they can be prepared and shipped at high specific surface areas and high silica concentrations.

- 5 The sols have improved capability to maintain the high specific surface area on storage at high silica concentrations. The silica-based sols and particles further result in very good or improved drainage and retention when used in conjunction with anionic, cationic and/or amphoteric organic polymers. Hereby the present invention makes it possible to increase the speed of the paper machine and to use a lower dosage of additives to give a
- 10 corresponding drainage and/or retention effect, thereby leading to an improved paper-making process and economic benefits. The invention thus relates to silica-based particles and an aqueous sol containing silica-based particles, herein also referred to as silica-based sol, and the production thereof, as further defined in the appended claims.

The present invention also relates to the use of the silica-based sols and

15 particles as drainage and retention aids in papermaking, preferably in combination with organic polymers as described herein, as further defined in the appended claims. The term "drainage and retention aid", as used herein, refers to one or more components (aids, agents or additives) which, when being added to a papermaking stock, give better drainage and/or retention than is obtained when not adding the components. The present

20 invention further relates to a process for the production of paper from an aqueous suspension containing cellulosic fibres, and optional fillers, which comprises adding to the suspension silica-based particles and at least one charged organic polymer, forming and draining the suspension on a wire. The invention thus relates to a process as further defined in the appended claims.

- 25 The silica-based sols according to the present invention are aqueous sols that contain anionic silica-based particles, i.e. particles based on silica (SiO_2) or silicic acid. The particles are preferably colloidal, i.e., in the colloidal range of particle size. The silica-based sols can have an S-value within the range of from 10 to 45%, suitably from 20 to 40% and preferably from 25 to 35%. The S-value can be measured and calculated as
- 30 described by Iler & Dalton in J. Phys. Chem. 60(1956), 955-957. The S-value indicates the degree of aggregate or microgel formation and a lower S-value is indicative of a higher degree of aggregation.

The silica-based sols can have a molar ratio of SiO_2 to M_2O , where M is alkali metal ion (e.g. Li, Na, K) and/or ammonium, within the range of from 10:1 to 40:1 suitably

35 from 12:1 to 35:1 and preferably from 15:1 to 30:1. The silica-based sols can have a pH of at least 10.0, suitably at least 10.5, preferably at least 10.6 and most preferably at

least 10.7. The pH can be up to about 11.5, suitably up to 11.0.

The silica-based sols should suitably have a silica content of at least 3% by weight but it is more suitable that the silica content is within the range of from 10 to 30% by weight and preferably from 12 to 20% by weight. In order to simplify shipping and
5 reduce transportation costs, it is generally preferable to ship high concentration silica-based sols but it is of course possible and usually preferable to dilute and mix the silica-based sols and particles with water to substantially lower silica contents prior to use, for example to silica contents of at least 0.05% by weight and preferably within the range of from 0.05 to 5% by weight, in order to improve mixing with the furnish components. The
10 viscosity of the silica-based sols can vary depending on, for example, the silica content of the sol. Usually, the viscosity is at least 5 cP, normally within the range of from 5 to 40 cP, suitably from 6 to 30 cP and preferably from 7 to 25 cP. The viscosity, which is suitably measured on sols having a silica content of at least 10% by weight, can be measured by means of known technique, for example using a Brookfield LVDV II+
15 viscosimeter. Preferred silica-based sols of this invention are stable. This means that these silica-based sols, when subjected to storage or ageing for one month at 20°C in dark and non-agitated conditions, exhibit only a small increase in viscosity, if any.

The silica-based particles present in the sol suitably have an average particle size below about 20 nm and preferably in the range of from about 1 to about 10 nm. As
20 conventional in silica chemistry, particle size refers to the average size of the primary particles, which may be aggregated or non-aggregated. The specific surface area of the silica-based particles is suitably at least 300 m²/g SiO₂ and preferably at least 550 m²/g. Generally, the specific surface area can be up to about 1050 m²/g and suitably up to 1000 m²/g. In a preferred embodiment of this invention, the specific surface area is within the
25 range of from 550 to 725 m²/g, preferably from 575 to 700 m²/g. In another preferred embodiment of this invention, the specific surface area is within the range of from 775 to 1050 m²/g. The specific surface area can be measured by means of titration with NaOH in known manner, e.g. as described by Sears in Analytical Chemistry 28(1956):12, 1981-1983 and in U.S. Patent No. 5,176,891, after appropriate removal of or adjustment for any
30 compounds present in the sample that may disturb the titration like aluminium and boron species. The term "specific surface area", as used herein, represents the average specific surface area of the silica-based particles and it is expressed as square metres per gram of silica (m²/g SiO₂).

In a preferred embodiment of the invention, the silica-based sol thus has an S-
35 value in the range of from 20 to 40%, a viscosity from 7 to 25 cP, a pH of at least 10.6, a molar ratio of SiO₂ to M₂O within the range of from 15 to 30, a silica content of at least

10% by weight, and contains colloidal anionic silica-based particles with a specific surface area within the range of from 550 to 1050 m²/g. Silica-based sols according to the invention with a silica content of from 15 to 20% by weight usually contain particles with a specific surface area within the range of from 550 to 725 m²/g whereas silica-based sols according to the invention with a silica content of from 10 to 15% by weight usually contain particles with a specific surface area within the range of from 775 to 1050 m²/g.

In a preferred embodiment of this invention, the silica-based sol is substantially free from aluminium, i.e. free from added modifiers containing aluminium. In another preferred embodiment of this invention, the silica-based sol is substantially free from boron, i.e. free from added modifiers containing boron. Minor amounts of such elements can however be present in the starting materials used to prepare the silica-based sols and particles. In yet another preferred embodiment of this invention, the silica-based sols are modified using various elements, e.g. aluminium and/or boron, which can be present in the aqueous phase and/or in the silica-based particles. If aluminium is used, the sols can have a molar ratio of Al₂O₃ to SiO₂ within the range of from 1:4 to 1:1500, suitably from 1:8 to 1:1000 and preferably from 1:15 to 1:500. If boron is used, the sols can have a molar ratio of B to SiO₂ within the range of from 1:4 to 1:1500, suitably from 1:8 to 1:1000 and preferably from 1:15 to 1:500. If both aluminium and boron are used, the molar ratio of Al to B can be within the range of from 100:1 to 1:100, suitably from 50:1 to 1:50.

The silica-based sols and particles according to the invention can be produced starting from a conventional aqueous silicate solution like alkali water glass, e.g. potassium or sodium water glass, preferably sodium water glass. The molar ratio of SiO₂ to M₂O, where M is alkali metal, e.g. sodium, potassium, ammonium, or a mixture thereof, in the silicate solution or water glass is suitably within the range of from 1.5:1 to 4.5:1, preferably from 2.5:1 to 3.9:1. Suitably a dilute silicate solution or water glass is used which can have an SiO₂ content of from about 3 to about 12% by weight, preferably from about 5 to about 10% by weight. The silicate solution or water glass, which usually has a pH around 13 or above 13, is acidified to a pH of from about 1 to about 4. The acidification can be carried out in known manner by addition of mineral acids, e.g. sulphuric acid, hydrochloric acid and phosphoric acid, or optionally with other chemicals known as suitable for acidification of water glass, e.g. ammonium sulphate and carbon dioxide. When adding a mineral acid, the acidification is suitably carried out in two steps, a first step to a pH of about 8 to 9, whereupon a certain ripening, i.e., a particle growth, is allowed to occur before further acidification to a pH of from about 1 to about 4. However, it is preferred that the acidification is carried out by means of an acid cation exchanger which, among other things, lead to more stable products. The acidification is preferably

carried out by means of a strongly acid cation exchange resin, for example of sulfonic acid type. It is preferred that the acidification is carried out to a pH of from about 2 to 4, most preferably from about 2.2 to 3.0. The product obtained, an acid sol or polysilicic acid, contains silica-based particles with a high specific surface area, normally above
5 1000 m²/g and usually around about 1300 m²/g.

The acid sol is then subjected to alkalisation, herein referred to as a first alkalisation step. The first alkalisation can be carried out by addition of conventional alkali, e.g. lithium hydroxide, sodium hydroxide, potassium hydroxide, ammonium hydroxide and mixtures thereof, and/or an aqueous silicate solution as defined above.
10 Potassium and sodium water glass, particularly sodium water glass, with a molar ratio of SiO₂ to M₂O as defined above, is suitably used in the alkalisation step. The SiO₂ content of the water glass solutions used for the first alkalisation is suitably within the range of from about 3 to about 35% by weight and preferably within the range of from 5 to 30% by weight. The first alkalisation is usually carried out to a pH of at least 6, suitably at least 7
15 and preferably at least 7.5, and the pH is usually up to 10.5, suitably up to 10.0. The first alkalisation is further suitably carried out to a final molar ratio of SiO₂ to M₂O, M being as defined above, within the range of from about 20:1 to about 80:1, preferably from 30:1 to 70:1. In the preparation of a sol as defined above the degree of microgel can be influenced in several ways and be controlled to a desired value. The degree of microgel
20 can be influenced by salt content, by adjustment of the concentration in the preparation of the acid sol and in the first alkalisation step since in this step the degree of microgel is influenced when the stability minimum for the sol is passed, at a pH of about 5. By prolonged times at this passage the degree of microgel can be directed to the desired value. It is particularly suitable to control the degree of microgel by adjustment of the dry
25 content, the SiO₂ content, in the first alkalisation step whereby a higher dry content gives a lower S-value. By keeping the SiO₂ content in the first alkalisation step within the range of from 4.5 to 8% by weight the S-value can be controlled to the desired values of, for example, from 10 to 45%. To obtain sols with S-values within the range of from 20 to 40% the SiO₂ content in the first alkalisation step is suitably kept within the range of from
30 5.0 to 7.5% by weight.

The silica-based particles present in the alkalisated sol obtained in the first alkalisation step is then subjected to particle growth so that particles with a lower specific surface area and higher stability are obtained. The particle growth process should suitably be carried out to provide silica-based particles with a specific surface area of at
35 least 300 m²/g and preferably at least 550 and up to about 1050 m²/g and suitably up to 1000 m²/g. In a preferred embodiment of this invention, the particle growth process is

carried out to provide a specific surface area within the range of from 550 to 725 m²/g. In another preferred embodiment of this invention, the particle growth process is carried out to provide a specific surface area within the range of from 775 to 1050 m²/g. The decrease in surface area can be obtained by storage at room temperature during somewhat longer times, a day up to about two days and nights, or, preferably, by heat treatment. In the heat treatment, times and temperatures can be adjusted so that shorter times are used at higher temperatures. Even if it of course is possible to use fairly high temperatures during very short times it is, from a practical point of view, more suitable to use lower temperatures during somewhat longer times. In the heat treatment, the alkalisol should suitably be heated at a temperature of at least 30°C, suitably from 35 to 95°C and preferably from 40 to 80°C. The heat treatment should suitably be carried out for at least 10 minutes, suitably from 15 to 600 minutes and preferably from 20 to 240 minutes.

After the particle growth step, and optional cooling, the obtained silica sol is again subjected to alkaalisation, herein referred to as a second alkaalisation step. The second alkaalisation can be carried out by addition of conventional alkali, e.g. lithium hydroxide, sodium hydroxide, potassium hydroxide, ammonium hydroxide and mixtures thereof, and/or an aqueous silicate solution as defined above. Potassium and sodium water glass, particularly sodium water glass, with a molar ratio of SiO₂ to M₂O as defined above, is suitably used in the second alkaalisation step. The SiO₂ content of the water glass solutions used for the second alkaalisation is suitably within the range of from about 3 to about 35% by weight and preferably within the range of from 5 to 30% by weight. The second alkaalisation is suitably carried out to a pH of at least 10.0, suitably at least 10.5, preferably at least 10.6 and most preferably at least 10.7. The pH can be up to about 11.5, suitably up to 11.0. The second alkaalisation is further suitably carried out to a final molar ratio of SiO₂ to M₂O, M being as defined above, within the range of from about 10:1 to 40:1 and suitably from 12:1 to 35:1, preferably from 15:1 to 30:1.

If desired, the process according to the invention can also comprise concentration of the silica-based sol obtained after the second alkaalisation. Alternatively, or additionally, the alkalisol obtained after the first alkaalisation but before the particle growth or heat treatment step, or the sol obtained after the particle growth or heat treatment step but before the second alkaalisation, can be subjected to concentration. Concentration can be carried out in known manner such as, for example, by osmotic methods, evaporation and ultrafiltration. The concentration is suitably carried out to achieve silica contents of at least 10% by weight, preferably from 10 to 30% by weight, and more preferably from 12 to 20% by weight.

If desired, the silica-based sol and particles can be modified by addition of

compounds containing, for example, aluminium and/or boron. Suitable aluminium-containing compounds include aluminates like sodium aluminate and potassium aluminate, suitably sodium aluminate. The aluminium-containing compound is suitably used in the form of an aqueous solution. Suitable boron-containing compounds include boric acid, borates like sodium and potassium borate, suitably sodium borate, tetraborates like sodium and potassium tetraborate, suitably sodium tetraborate, and metaborates like sodium and potassium metaborate. The boron-containing compound is suitably used in the form of an aqueous solution.

When using an aluminium-containing compound in the process, it is suitable to add it to the sol subjected to particle growth or heat treatment, either before or after the second alkalisation step. Alternatively, or additionally, the aluminium-containing compound can be added to the silicate solution to be acidified, to the acid sol or to the alkalised sol obtained in the first alkalisation step before the particle growth or heat treatment step. The aluminium-containing compound can be added in admixture with acid in the acidification step and in admixture with alkali or silicate solution in any of the alkalisation steps. The aluminium-containing compound is suitably added in an amount such that the obtained sol has a molar ratio of Al_2O_3 to SiO_2 as defined above,

When using a boron-containing compound in the process, it is suitable to add it to the sol subjected to particle growth or heat treatment, either before or after the second alkalisation step. Alternatively, or additionally, the boron-containing compound can be added to the silicate solution to be acidified, to the acid sol or to the alkalised sol obtained in the first alkalisation step before the particle growth or heat treatment step. The boron-containing compound can be added in admixture with acid in the acidification step and in admixture with alkali or silicate solution in any of the alkalisation steps. The boron-containing compound is suitably added in an amount such that the obtained sol has a molar ratio of B to SiO_2 as defined above. If both aluminium-containing and boron-containing compounds are used, they are suitably added in amounts such that the obtained sol has a molar ratio of Al to B suitably as defined above.

If the sol, before any aluminium and/or boron modification, contains too high amounts of alkali metal ions or ammonium ions, it is preferable to remove at least part of these ions, for example by ion exchange, to provide silica-based sols with a final molar ratio of SiO_2 to M_2O within the desired range as defined above.

According to the present process, silica-based sols having silica contents of from 10 to 30% by weight, suitably from 12 to 20% by weight, and viscosities of at least 5 cP, normally within the range of from 5 to 40 cP, suitably from 6 to 30 cP and preferably from 7 to 25 cP, after optional concentration, can be prepared and the produced sols

exhibit good storage stability and can be stored for several months without any substantial decrease of the specific surface area and without gel formation.

The silica-based sols and particles of this invention are suitable for use as flocculating agents, for example in the production of pulp and paper, notably as drainage and retention aids, and within the field of water purification, both for purification of different kinds of waste water and for purification specifically of white water from the pulp and paper industry. The silica-based sols and particles can be used as flocculating agents, notably as drainage and retention aids, in combination with organic polymers which can be selected from anionic, amphoteric, non-ionic and cationic polymers and mixtures thereof, herein also referred to as "main polymer". The use of such polymers as flocculating agents and as drainage and retention aids is well known in the art. The polymers can be derived from natural or synthetic sources, and they can be linear, branched or cross-linked. Examples of generally suitable main polymers include anionic, amphoteric and cationic starches, anionic, amphoteric and cationic guar gums, and anionic, amphoteric and cationic acrylamide-based polymers, as well as cationic poly(diallyldimethyl ammonium chloride), cationic polyethylene imines, cationic polyamines, polyamidoamines and vinylamide-based polymers, melamine-formaldehyde and urea-formaldehyde resins. Suitably the silica-based sols are used in combination with at least one cationic or amphoteric polymer, preferably cationic polymer. Cationic starch and cationic polyacrylamide are particularly preferred polymers and they can be used singly, together with each other or together with other polymers, e.g. other cationic polymers or anionic polyacrylamide. The molecular weight of the main polymer is suitably above 1,000,000 and preferably above 2,000,000. The upper limit is not critical; it can be about 50,000,000, usually 30,000,000 and suitably about 25,000,000. However, the molecular weight of polymers derived from natural sources may be higher.

When using the silica-based sols and particles in combination with main polymer(s) as mentioned above, it is further preferred to use at least one low molecular weight (hereinafter LMW) cationic organic polymer, commonly referred to and used as anionic trash catchers (ATC). ATC's are known in the art as neutralizing and/or fixing agents for detrimental anionic substances present in the stock and the use thereof in combination with drainage and retention aids often provide further improvements in drainage and/or retention. The LMW cationic organic polymer can be derived from natural or synthetic sources, and preferably it is an LMW synthetic polymer. Suitable organic polymers of this type include LMW highly charged cationic organic polymers such as polyamines, polyamidoamines, polyethyleneimines, homo- and copolymers based on diallyldimethyl ammonium chloride, (meth)acrylamides and (meth)acrylates. In relation to the

WO 00/66491

PCT/SE00/00821

molecular weight of the main polymer, the molecular weight of the LMW cationic organic polymer is preferably lower; it is suitably at least 1,000 and preferably at least 10,000. The upper limit of the molecular weight is usually about 700,000, suitably about 500,000 and usually about 200,000. Preferred combinations of polymers that can be co-used with the
5 silica-based sols of this invention include LMW cationic organic polymer in combination with main polymer(s), such as, for example, cationic starch and/or cationic polyacrylamide, anionic polyacrylamide as well as cationic starch and/or cationic polyacrylamide in combination with anionic polyacrylamide.

The components of the drainage and retention aids according to the invention
10 can be added to the stock in conventional manner and in any order. When using drainage and retention aids comprising silica-based particles and an organic polymer, e.g. a main polymer, it is preferred to add the polymer to the stock before adding the silica-based particles, even if the opposite order of addition may be used. It is further preferred to add the main polymer before a shear stage, which can be selected from
15 pumping, mixing, cleaning, etc., and to add the silica-based particles after that shear stage. LMW cationic organic polymers, when used, are preferably introduced into the stock prior to introducing the main polymer. Alternatively, the LMW cationic organic polymer and the main polymer can be introduced into stock essentially simultaneously, either separately or in admixture, for example as disclosed in U.S. Patent No. 5,858,174, which is hereby
20 incorporated herein by reference. The LMW cationic organic polymer and the main polymer are preferably introduced into the stock prior to introducing the silica-based sol.

In a preferred embodiment of this invention, the silica-based sols and particles are used as drainage and retention aids in combination with at least one organic polymer, as described above, and at least one aluminium compound. Aluminium compounds can be
25 used to further improve the drainage and/or retention performance of stock additives comprising silica-based particles. Suitable aluminium salts include alum, aluminates, aluminium chloride, aluminium nitrate and polyaluminium compounds, such as polyaluminium chlorides, polyaluminium sulphates, polyaluminium compounds containing both chloride and sulphate ions, polyaluminium silicate-sulphates, and mixtures thereof. The
30 polyaluminium compounds may also contain other anions, for example anions from phosphoric acid, organic acids such as citric acid and oxalic acid. Preferred aluminium salts include sodium aluminate, alum and polyaluminium compounds. The aluminium compound can be added before or after the addition of the silica-based particles. Alternatively, or additionally, the aluminium compound can be added simultaneously with the silica-based
35 sol at essentially the same point, either separately or in admixture with it, for example as disclosed by U.S. Patent No 5,846,384 which is hereby incorporated herein by reference. In

many cases, it is often suitable to add an aluminium compound to the stock early in the process, for example prior to the other additives.

The components of the drainage and retention aids according to the invention are added to the stock to be dewatered in amounts which can vary within wide limits depending on, inter alia, type and number of components, type of furnish, filler content, type of filler, point of addition, etc. Generally the components are added in an amount that give better drainage and/or retention than is obtained when not adding the components. The silica-based sol and particles are usually added in an amount of at least 0.001% by weight, often at least 0.005% by weight, calculated as SiO_2 and based on dry stock substance, i.e. cellulosic fibres and optional fillers, and the upper limit is usually 1.0% and suitably 0.5% by weight. The main polymer is usually added in an amount of at least 0.001%, often at least 0.005% by weight, based on dry stock substance, and the upper limit is usually 3% and suitably 1.5% by weight. When using an LMW cationic organic polymer in the process, it can be added in an amount of at least 0.05%, based on dry substance of the stock to be dewatered. Suitably, the amount is in the range of from 0.07 to 0.5%, preferably in the range from 0.1 to 0.35%. When using an aluminium compound in the process, the total amount introduced into the stock to be dewatered depends on the type of aluminium compound used and on other effects desired from it. It is for instance well known in the art to utilise aluminium compounds as precipitants for rosin-based sizing agents. The total amount added is usually at least 0.05%, calculated as Al_2O_3 and based on dry stock substance. Suitably the amount is in the range of from 0.1 to 3.0%, preferably in the range from 0.5 to 2.0%.

Further additives which are conventional in papermaking can of course be used in combination with the additives according to the invention, such as, for example, dry strength agents, wet strength agents, optical brightening agents, dyes, sizing agents like rosin-based sizing agents and cellulose-reactive sizing agents, e.g. alkyl and alkenyl ketene dimers and ketene multimers, alkyl and alkenyl succinic anhydrides, etc. The cellulosic suspension, or stock, can also contain mineral fillers of conventional types such as, for example, kaolin, china clay, titanium dioxide, gypsum, talc and natural and synthetic calcium carbonates such as chalk, ground marble and precipitated calcium carbonate.

The process of this invention is used for the production of paper. The term "paper", as used herein, of course include not only paper and the production thereof, but also other cellulosic fibre-containing sheet or web-like products, such as for example board and paperboard, and the production thereof. The process can be used in the production of paper from different types of suspensions of cellulose-containing fibres and the suspensions should suitably contain at least 25% by weight and preferably at least 50% by

weight of such fibres, based on dry substance. The suspension can be based on fibres from chemical pulp such as sulphate, sulphite and organosolv pulps, mechanical pulp such as thermomechanical pulp, chemo-thermomechanical pulp, refiner pulp and groundwood pulp, from both hardwood and softwood, and can also be based on recycled fibres, optionally from de-inked pulps, and mixtures thereof. The pH of the suspension, the stock, can be within the range of from about 3 to about 10. The pH is suitably above 3.5 and preferably within the range of from 4 to 9.

The invention is further illustrated in the following Examples which, however, are not intended to limit the same. Parts and % relate to parts by weight and % by weight, respectively, unless otherwise stated.

Example 1

A standard silica sol was prepared as follows:

762.7 g sodium water glass with a molar ratio of SiO_2 to Na_2O of 3.3 and SiO_2 content of 27.1% was diluted with water to 3000 g yielding a silicate solution (I) with a SiO_2 content of 6.9% by weight. 2800 g of this silicate or water glass solution was passed through a column filled with a strong cation exchange resin saturated with hydrogen ions. 2450 g of ion-exchanged water glass or polysilicic acid (II) with an SiO_2 content of 6.5% by weight and a pH of 2.4 was collected from the ion exchanger. 1988 g of the polysilicic acid (II) was fed into a reactor and diluted with 12.3 g water. 173.9 g of the 6.9% silicate solution (I) was then added under vigorous agitation. The resulting solution was then heated at 85°C for 60 minutes and then cooled to 20°C. The obtained silica sol (1a) had the following characteristics:

Sol 1a (ref.): SiO_2 content = 7.3% by weight, molar ratio $\text{SiO}_2/\text{Na}_2\text{O}$ = 40, pH = 10.2, S-value = 29%, viscosity = 2.2 cP and specific surface area of the particles = 530 m^2/g .

Two further silica sols, Sol 1b and Sol 1c, were produced which had the following characteristics:

Sol 1b (ref.): SiO_2 content = 7.3% by weight, molar ratio $\text{SiO}_2/\text{Na}_2\text{O}$ = 63, pH = 10.0, S-value = 26, viscosity = 2.7 cP and specific surface area of the particles = 500 m^2/g .

Sol 1c (ref.): SiO_2 content = 5.4% by weight, molar ratio $\text{SiO}_2/\text{Na}_2\text{O}$ = 35, pH = 9.8, S-value = 32, viscosity = 1.6 cP and specific surface area of the particles = 690 m^2/g .

Example 2

Six sols of silica-based particles according to the invention was prepared from a polysilicic acid similar to the polysilicic acid (II) produced with the same ion exchange process and with an SiO₂ content of 5.46% by weight. To 102.0 kg of the polysilicic acid
 5 was added 1.46 kg of sodium water glass with a ratio SiO₂/Na₂O of 3.3 under vigorous agitation resulting in a solution with a molar ratio SiO₂/Na₂O of 54.0. This solution was heat treated at 60°C for 2 h 20 min and cooled to 20°C whereupon the product was concentrated to a SiO₂ content of 15.6% by weight. This intermediate sol product was now divided into six separate samples, a to f. Samples a to c were further alkalisied with
 10 NaOH, samples d to f with water glass, to achieve sols with a molar ratio SiO₂/Na₂O between 21.5 and 34.0 and a silica content of about 15.0% by weight. The obtained sols of silica-based particles had the characteristics set forth in Table 1:

Table 1

15	Sol	Molar ratio	pH	S-value	Viscosity	Spec. Surface Area
		[SiO ₂ /Na ₂ O]				
	Sol 2a	21.5	10.7	31	17	720
	Sol 2b	28.0	10.3	30	29	710
	Sol 2c	34.0	10.0	29	40	690
20	Sol 2d	21.5	10.7	31	20	680
	Sol 2e	28.0	10.3	29	34	670
	Sol 2f	33.0	10.0	29	38	680

Example 3

25 A polysilicic acid (II) produced with the above ion exchange process and alkalisied with water glass to a molar ratio SiO₂/Na₂O of 54.0 as in Example 2 was heat treated at 60°C for 1 h. To 58 kg of this product was added 7.25 kg of diluted water glass with a molar ratio SiO₂/Na₂O of 3.3 and silica content 5.5% by weight. The resulting sol of silica-based particles, Sol 3, was concentrated to a silica content of 15.2% by weight and
 30 had a molar ratio SiO₂/Na₂O = 24, pH 10.7, S-value = 34, viscosity = 9.0 cp and specific surface area of the particles = 760 m²/g.

Example 4

1000 g polysilicic acid (II) with an SiO₂ content of 5.5% by weight was mixed with
 35 14.5 g water glass solution with an SiO₂ content of 27.1% by weight and a molar ratio SiO₂/Na₂O = 3.3 under vigorous agitation resulting in a product with a molar ratio

13

SiO₂/Na₂O of 51 and a silica content of 5.8% by weight SiO₂, which was heat treated at 60°C for 1.5 h and then concentrated to a silica content of 16.7% by weight SiO₂. 283 g of the product obtained was mixed with 33.0 g NaOH resulting in a sol of silica-based particles, Sol 4, with SiO₂ content = 15.2% by weight, molar ratio SiO₂/Na₂O = 21, pH = 10.6, S-value = 32%, viscosity = 14.2 cP and specific surface area of the particles = 720 m²/g.

Example 5

The general procedure according to Example 3 was followed except that the heat treatment was carried for 1.25 h and concentration was carried out to higher silica contents. Two sols of silica-based particles were prepared; Sol 5a and Sol 5b. Sol 5a had SiO₂ content = 18% by weight, molar ratio SiO₂/Na₂O = 18, pH = 10.7, S-value = 36%, viscosity = 18 cP and specific surface area of the particles = 700 m²/g. Sol 5b had SiO₂ content = 20% by weight, molar ratio SiO₂/Na₂O = 18.3, pH = 10.7, S-value = 37%, viscosity = 31 cP and specific surface area of the particles = 700 m²/g.

Example 6

Drainage performance was evaluated by means of a Dynamic Drainage Analyser (DDA), available from Akribi, Sweden, which measures the time for draining a set volume of stock through a wire when removing a plug and applying vacuum to that side of the wire opposite to the side on which the stock is present.

The stock used was based on a blend of 60% bleached birch sulphate and 40% bleached pine sulphate to which was added 30% ground calcium carbonate as a filler. Stock volume was 800 ml, consistency 0.25 % and pH about 8.0. Conductivity of the stock was adjusted to 0.47 mS/cm by addition of sodium sulphate.

In the tests, silica-based sols were used in conjunction with a cationic polymer, Raisamyl 142, which is a conventional medium-high cationised starch having a degree of substitution of 0.042, which was added to the stock in an amount of 12 kg/tonne, calculated as dry starch on dry stock system. Silica-based sols according to Examples 1 to 4 were tested in this Example. In addition, Sols 6a and 6b were also tested for comparison purposes. Sol 6a is a commercial silica sol with an S-value = 45%, SiO₂ content = 15.0% by weight, molar ratio SiO₂/Na₂O = 40, viscosity = 3.0 cP, specific surface area of the particles = 500 m²/g. Sol 6b is another commercial silica sol with an S-value = 36%, SiO₂ content = 10.0% by weight, molar ratio SiO₂/Na₂O = 10, viscosity = 2.5 cP, specific surface area of the particles = 880 m²/g. The silica-based sols were added in an amount of 0.5 kg/ton, calculated as SiO₂ and based on dry stock system.

The stock was stirred in a baffled jar at a speed of 1500 rpm throughout the test and chemical additions were conducted as follows: i) adding cationic starch to the stock following by stirring for 30 seconds, ii) adding silica-based sol to the stock followed by stirring for 15 seconds, iii) draining the stock while automatically recording the drainage time.

Drainage times for the different silica-based sols are shown in Table 2:

Table 2

Silica-based sol	Dewatering time	
	[sec]	
Sol 1a (ref.)	12.0	
Sol 1b (ref.)	11.1	
Sol 1c (ref.)	12.0	
Sol 2d	9.7	
Sol 3	9.5	
Sol 4	9.4	
Sol 6a (ref.)	12.0	
Sol 6b (ref.)	9.8	

Example 7

Drainage performance was evaluated according to the general procedure of Example 6 except that the stock had a consistency of 0.3% and pH about 8.5. Retention performance was evaluated by means of a nephelometer by measuring the turbidity of the filtrate, the white water, obtained by draining the stock.

Silica-based sols according to Example 5 according to the invention were tested against Sol 6a used for comparison. Table 3 shows the drainage time obtained at various dosages (kg/ton) of silica-based particles, calculated as SiO₂ and based on dry stock system. The addition of only cationic starch (12 kg/tonne, calculated as dry starch on dry stock system) resulted in a drainage time of 15.8 sec.

Table 3

Silica-based sol	Drainage time (sec) / Turbidity (NTU) at SiO ₂ dosage of				
	0.5 kg/t	1.0 kg/t	1.5 kg/t	2.0 kg/t	3.0 kg/t
Sol 6a (ref.)	11.1/-	8.8/59	7.9/58	7.1/54	6.8/60
Sol 5a	9.0/-	7.1/52	6.3/50	5.2/52	5.7/53
Sol 5b	8.9/-	6.9/-	6.3/-	5.7/-	6.0/-

Claims

1. Aqueous sol containing silica-based particles, characterised in that it has an S-value within the range of from 10 to 45%, a viscosity within the range of from 5 to 40 cP and a molar ratio of SiO_2 to M_2O , where M is alkali metal or ammonium, within the range of from 10:1 to 40:1.
2. Aqueous sol containing silica-based particles, characterised in that it has an S-value within the range of from 10 to 45%, a viscosity within the range of from 5 to 40 cP and a silica content of at least 10% by weight.
3. Aqueous sol according to claim 1, characterised in that it has a silica content of at least 10% by weight..
4. Aqueous sol according to claim 1, 2 or 3, characterised in that the silica-based particles have a specific surface area within the range of from 775 to 1050 m^2/g .
5. Aqueous sol according to claim 1, 2 or 3, characterised in that the silica-based particles have a specific surface area within the range of from 550 to 725 m^2/g .
6. Aqueous sol according to any of claims 1 to 5, characterised in that the S-value is within the range of from 20 to 40%.
7. Aqueous sol according to any of claims 1 to 6, characterised in that the viscosity is within the range of from 7 to 25 cP.
8. Aqueous sol according to any of claims 1 to 7, characterised in that it has a molar ratio of SiO_2 to M_2O , where M is alkali metal or ammonium, within the range of from 15:1 to 30:1.
9. Aqueous sol according to any of claims 1 to 8, characterised in that it has a pH of at least 10.6.
10. Process for the production of silica-based particles, characterised in that it comprises the steps of
 - (a) acidifying an aqueous silicate solution to a pH of from 1 to 4 to form an acid sol,
 - (b) alkalisng the acid sol at an SiO_2 content within the range of from 4.5 to 8% by weight to a pH of at least 7,
 - (c) allowing particle growth of the alkalisng sol for at least 10 minutes, and then
 - (d) alkalisng the obtained sol to a pH of at least 10.0.
11. Process for the production of silica-based particles, characterised in that it comprises the steps of
 - (a) acidifying an aqueous silicate solution to a pH of from 1 to 4 to form an acid sol,
 - (b) alkalisng the acid sol at an SiO_2 content within the range of from 4.5 to 8% by weight,

- (c) heat-treating the alkalisol at a temperature of at least 30°C, and then
(d) alkalisol the heat-treated sol to a pH of at least 10.0.

12. Process according to claim 10 or 11, characterised in that the
alkalisation according to (b) and (d) is carried out by means of an aqueous silicate
5 solution.

13. Process according to claim 10, 11 or 12, characterised in that
the particle growth and heat-treatment according to (c) is carried out at a temperature
within the range of from 35 to 95°C.

14. Process according to claim 10, 11, 12 or 13, characterised in
10 that the particle growth and heat-treatment according to (c) is carried out for 20 to 240
minutes.

15. Process according to any of claims 10 to 14, characterised in
that the alkalisation according to (d) produces a silica-based sol having a molar ratio of
SiO₂ to M₂O, where M is alkali metal or ammonium, within the range of from 15:1 to 30:1
15 and a pH of at least 10.6.

16. Silica-based particles obtainable by a process according to any of claims 10
to 15.

17. Use of silica-based particles according to any of claims 1 to 9 or 16 or
produced by a process according to any of claims 10 to 15 as drainage and retention
20 aids in the production of paper.

18. Process for the production of paper from an aqueous suspension containing
cellulosic fibres, and optional fillers, which comprises adding to the suspension silica-based
particles and at least one charged organic polymer, forming and draining the suspension on
a wire, characterised in that the silica-based particles are present in an
25 aqueous sol according to any of claims 1 to 9 or produced by a process according to any
of claims 10 to 15.

19. Process according to claim 18, characterised in that the charged
organic polymer is cationic starch or cationic polyacrylamide.

20. Process according to claim 18 or 19, characterised in that before
30 adding the silica-based particles to the suspension the silica-based particles are diluted
or mixed with water to form an aqueous sol having a silica content of from 0.05 to 5% by
weight.

21. Process according to any of claims 18 to 20, characterised in
that the silica-based particles are added to the suspension in an amount of from 0.005 to
35 0.5% by weight, calculated as SiO₂ and based on dry cellulosic fibres and optional fillers.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/SE 00/00821

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C01B33/143 C01B33/146 D21H21/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C01B D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, PAJ, INSPEC, COMPENDEX, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 94 05596 A (EKA NOBEL AB) 17 March 1994 (1994-03-17) the whole document & US 5 603 805 A 18 February 1997 (1997-02-18) cited in the application	1-21
A	WO 91 07350 A (EKA NOBEL AB) 30 May 1991 (1991-05-30) claims 1-10 * examples * page 2, line 18 -page 7, line 14 & US 5 318 833 A 29 November 1994 (1994-11-29) cited in the application	1-21
A		

-/-



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

25 August 2000

Date of mailing of the international search report

31/08/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Rigondaud, B

INTERNATIONAL SEARCH REPORT

International Application No

PCT/SE 00/00821

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 94 05595 A (EKA NOBEL AB) 17 March 1994 (1994-03-17) claims 1-10 examples 1-10	1-4,6,7, 18
A	& US 5 607 552 A 4 March 1997 (1997-03-04) cited in the application	
A	US 2 750 345 A (GUY B. ALEXANDER) 12 June 1956 (1956-06-12) examples 1,3	10-14,16
A	GB 663 013 A (MONSANTO CHEMICAL COMPANY) claims 1-12	10-14,16
A	US 3 083 167 A (RICHARD F. SHANNON) 26 March 1963 (1963-03-26) claims 1-6	10,16
A	BE 507 441 A (E. I. DU PONT DE NEMOURS AND COMPANY)	
A	WO 96 01787 A (RHONE POULENC CHIMIE) 25 January 1996 (1996-01-25)	

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/SE 00/00821

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9405596 A	17-03-1994	SE 501214 C	12-12-1994
		AT 138354 T	15-06-1996
		AU 667966 B	18-04-1996
		AU 4988193 A	29-03-1994
		BR 9306878 A	08-12-1998
		CA 2141551 A	17-03-1994
		CN 1084490 A,B	30-03-1994
		DE 69302823 D	27-06-1996
		DK 656872 T	07-10-1996
		EP 0656872 A	14-06-1995
		ES 2087767 T	16-07-1996
		FI 950622 A	13-02-1995
		JP 2787377 B	13-08-1998
		JP 8502016 T	05-03-1996
		MX 9305272 A	28-02-1994
		NO 950738 A	27-02-1995
		NZ 255615 A	27-11-1995
		RU 2081060 C	10-06-1997
		SE 9202502 A	01-03-1994
		US 5603805 A	18-02-1997
WO 9107350 A	30-05-1991	SE 500387 C	13-06-1994
		AT 107608 T	15-07-1994
		AU 628692 B	17-09-1992
		AU 6733490 A	13-06-1991
		BR 9007822 A	01-09-1992
		CA 2067506 A,C	09-05-1991
		CN 1115817 A,B	31-01-1996
		DE 69010210 D	28-07-1994
		DE 69010210 T	13-10-1994
		DK 491879 T	07-11-1994
		EP 0491879 A	01-07-1992
		ES 2055581 T	16-08-1994
		FI 922056 A,B,	06-05-1992
		JP 4505314 T	17-09-1992
		JP 5009368 B	04-02-1993
		KR 9505762 B	30-05-1995
		LT 445 A,B	25-10-1994
		LV 10227 A,B	20-10-1994
		NO 921848 A	11-05-1992
		NZ 235963 A	26-05-1992
		PT 95849 A,B	13-09-1991
		SE 8903753 A	10-05-1991
		RU 2068809 C	10-11-1996
		US 5643414 A	01-07-1997
		US 5368833 A	29-11-1994
WO 9405595 A	17-03-1994	SE 501216 C	12-12-1994
		AT 150427 T	15-04-1997
		AU 665651 B	11-01-1996
		AU 4988293 A	29-03-1994
		BR 9306825 A	08-12-1998
		CA 2141550 A,C	17-03-1994
		CN 1089675 A,B	20-07-1994
		CZ 9500495 A	14-02-1996
		DE 69309073 D	24-04-1997
		DE 69309073 T	10-07-1997
		DK 656871 T	22-09-1997

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/SE 00/00821

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9405595 A		EP 0656871 A ES 2098774 T FI 950585 A JP 2751085 B JP 8500573 T KR 204398 B MX 9305273 A NO 950737 A NZ 255616 A PL 307681 A RU 2108970 C SE 9202501 A US 5607552 A ZA 9306355 A	14-06-1995 01-05-1997 10-02-1995 18-05-1998 23-01-1996 15-06-1999 28-02-1994 27-02-1995 26-09-1995 12-06-1995 20-04-1998 01-03-1994 04-03-1997 25-03-1994
US 2750345 A	12-06-1956	NONE	
GB 663013 A		NONE	
US 3083167 A	26-03-1963	NONE	
BE 507441 A		NONE	
WO 9601787 A	25-01-1996	FR 2722185 A AU 696633 B AU 2929995 A BR 9508239 A CA 2193002 A CN 1152292 A, B EP 0768986 A JP 9510686 T KR 197149 B NO 970033 A NZ 289450 A RU 2137711 C ZA 9505622 A	12-01-1996 17-09-1998 09-02-1996 23-12-1997 25-01-1996 18-06-1997 23-04-1997 28-10-1997 15-06-1999 07-03-1997 26-02-1998 20-09-1999 01-06-1997